



VULKOSOFT®

VULKOLLAN® is a highly elastic polyurethane elastomer based on Desmodur® 15. Like all VULKOLLAN® versions, the material has excellent mechanical properties including good dynamic load capacity, good abrasion resistance and tear growth resistance, high impact resilience and low compression set. With a Shore hardness of 85° Shore A, VULKOSOFT® combines high load capacity with good noise reduction and vibration damping and is therefore particularly suitable for

use on surfaces where care is needed, for example on tiled floors.

- Medium load capacities
- Medium speeds
- Good noise reduction and vibration damping
- Floor preserving

Technical Informationen	Standards	Unit	
Shore hardness A	ISO 7619	- -	85 ° (± 3)
Density	ISO 1183	g/cm ³	approx. 1,2
Elongation at break	DIN 53 504	%	approx. 607
Stress value at 100%	DIN 53 504	MPa	8,0 - 8,5
Rebound resilience	DIN 53 512	%	55 - 60
Determination of tear strength	ISO 34	kN/m	43 - 47
Compression set 70 h, 23°C	ISO 815	%	9,0 - 11
Abrasion resistance	ISO 4649	mm ³	40
Coefficient of friction (traction) on wet floor at 8000 N		- -	0,11
Rolling resistance at 20°C of charge (average)		%	0,85 - 0,95
Starting resistance at 20°C of charge (average)		%	1,13 - 1,43

All values indicated in this table are approximative values resulting from our own tests or information given by our raw material suppliers. The standardised tests refer to special test samples. Therefore these values are not directly applicable to wheels and castors. Furthermore these values change under such influences as temperature, humidity, duration of charge, rate of deformation, etc. For more information please visit www.raedervogel.de.

No legal obligation.