

Technical Information

VULKODYN® 94° Shore A



RÄDER-VOGEL®
FOR BETTER WHEELS AND BETTER SERVICE

Mechanical features

Shore hardness A	DIN 53 505	94°
Density in g/cm³	DIN 53 479	1,16
Elongation at rupture in %	DIN 53 504	approx. 670
Tensile stress in MPa at 100%	DIN 53 504	9,5 - 10,0
Modulus of elasticity in MPa at 20°C	DIN 53 457	70 - 80
Impact resilience in %	DIN 53 512	65 - 70
Resistance to tear propagation in kN/m	DIN 53 515	65 - 70
Compression set in % 70 h, 23°C	DIN 53 517	9 - 10
Abrasion loss in mm³	DIN 53 516	35
Coefficient of friction (traction) on wet floor at 8000 N		0,11
Rolling resistance at 20°C in % of charge	(average)	0,65 - 0,7
Starting resistance at 20°C in % of charge	(average)	0,95 - 1,0

VULKODYN® = registered trade mark of RÄDER-VOGEL®

All values indicated in this table are approximative values resulting from our own tests or informations given by our raw material suppliers.

The normed values refer to special test samples, so that these values are not directly applicable for wheels and castors. Furthermore these values change under such influences as temperature, humidity, duration of charge, compression, etc.

No legal obligation.

For more information, please visit:

www.raedervogel.de/en/wheel-materials/vulkodyn.html

July 2010

RÄDER-VOGEL® • RÄDER- UND ROLLENFABRIK GMBH & CO. KG • SPERLSDEICHER WEG 19 - 23 • 21109 HAMBURG

TEL.: +49 40 75499-0 • FAX: +49 40 75499-175 • WWW.RAEDEROVAGEL.DE • RV@RAEDEROVAGEL.DE

KOMMANDITGESELLSCHAFT SITZ HAMBURG, HR HAMBURG A 53909, PERS. HAFT. GES.: RV RÄDER- UND ROLLENFABRIK GMBH
SITZ HAMBURG, HR HAMBURG B 24587 • GESCHÄFTSFÜHRENDE GESELLSCHAFTER: DIPL.-VOLKSWIRT DIETER HENNING,
DIPL.-KAUFMANN (FH) CARSTEN HENNING • UST-ID-NR. DE 118 238 838